



Specification Sheet

Black Natural Rubber

General Information

Compound Number:	060R0134
Date:	December 09, 2022
Origin:	Made in the USA
Polymer:	Natural Rubber
Temperature Range:	-40 to +160°F
Specification:	ASTM D2000 M1AA617
Compliance:	REACH , RoHS & Prop. 65

Physical Properties

Property	Test Method	Required
Hardness, Shore A	ASTM D2240	60 ± 5
Tensile, psi	ASTM D412	2500
Elongation, %	ASTM D412	400

West American Rubber Company, LLC
750 North Main Street, Orange, CA 92868
Tel: 714-532-3355 Fax: 714-532-2238
Email: Sales@warco.com

America's Choice for Quality Rubber Since 1910™
Where Tradition Meets Innovation™

Because WARCO cannot anticipate or control the many different conditions under which this information and/or product may be used, it does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. Users of WARCO products should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties but they should not be used to establish specification limits or used alone as the basis of design. Please visit warco.com/terms for complete Terms and Conditions of Sale.