

# Specification Sheet

## Fluorozone Premium Performance FKM

### General Information

|                    |                            |
|--------------------|----------------------------|
| Compound Number:   | 075F0205                   |
| Date:              | December 09, 2022          |
| Origin:            | Made in the USA            |
| Polymer:           | FKM (Fluoroelastomer)      |
| Temperature Range: | -20 to +400°F              |
| Specification:     |                            |
| Compliance:        | RoHS & REACH & CA. Prop 65 |

### Physical Properties

| Property          | Test Method | Typical |
|-------------------|-------------|---------|
| Hardness, Shore A | ASTM D2240  | 75 ± 5  |
| Tensile, psi      | ASTM D412   | 1200    |
| Elongation, %     | ASTM D412   | 300     |

West American Rubber Company, LLC  
750 North Main Street, Orange, CA 92868  
Tel: 714-532-3355 Fax: 714-532-2238  
Email: [Sales@warco.com](mailto:Sales@warco.com)

America's Choice for Quality Rubber Since 1910™  
Where Tradition Meets Innovation™

Because WARCO cannot anticipate or control the many different conditions under which this information and/or product may be used, it does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. Users of WARCO products should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties but they should not be used to establish specification limits or used alone as the basis of design. Please visit [warco.com/terms](http://warco.com/terms) for complete Terms and Conditions of Sale.