



# Specification Sheet

## Peroxide cure EPDM

### General Information

Compound Number:	040K0175
Date:	December 12, 2022
Origin:	Made in the USA
Polymer:	EPDM (Ethylene-propylene rubber)
Temperature Range:	-67 to +300°F
Specification:	ASTM D2000 M4CA410 A25 B35 C32 EA14 F19
Compliance:	RoHS, REACH and Prop 65 CA.

### Physical Properties

Property	Test Method	Required
Hardness, Shore A	ASTM D2240	40 ± 5
Tensile, psi	ASTM D412	1450
Elongation, %	ASTM D412	400

West American Rubber Company, LLC  
 750 North Main Street, Orange, CA 92868  
 Tel: 714-532-3355 Fax: 714-532-2238  
 Email: [Sales@warco.com](mailto:Sales@warco.com)

America's Choice for Quality Rubber Since 1910™  
 Where Tradition Meets Innovation™