



Specification Sheet

Peroxide Cure EPDM

General Information

Compound Number:	060K0190
Date:	December 09, 2022
Origin:	Made in the USA
Polymer:	EPDM (Ethylene-propylene rubber)
Temperature Range:	-67 to +275°F
Specification:	ASTM D2000 M4CA610 A25 B35 C32 EA14 F19
Compliance:	REACH, RoHS, Prop 65

Physical Properties

Property	Test Method	Required
Hardness, Shore A	ASTM D2240	60 ± 5
Tensile, psi	ASTM D412	1450
Elongation, %	ASTM D412	300

West American Rubber Company, LLC
 750 North Main Street, Orange, CA 92868
 Tel: 714-532-3355 Fax: 714-532-2238
 Email: Sales@warco.com

America's Choice for Quality Rubber Since 1910™
 Where Tradition Meets Innovation™