



# Specification Sheet

## 100% FKM Commercial Viton A: 66% Fluorine

### General Information

Compound Number:	070F0074
Date:	December 09, 2022
Origin:	Made in the USA
Polymer:	FKM (Fluoroelastomer)
Temperature Range:	-20 to +400°F
Specification:	Cinnamon Scented
Compliance:	RoHS & REACH & CA. Prop 65, Manufactured with genuine Chemours Viton.

### Physical Properties

Property	Test Method	Minimum
Hardness, Shore A	ASTM D2240	70 ± 5
Tensile, psi	ASTM D412	800
Elongation, %	ASTM D412	175

West American Rubber Company, LLC  
 750 North Main Street, Orange, CA 92868  
 Tel: 714-532-3355 Fax: 714-532-2238  
 Email: [Sales@warco.com](mailto:Sales@warco.com)

America's Choice for Quality Rubber Since 1910™  
 Where Tradition Meets Innovation™