



# Specification Sheet

## 100% FKM Commercial Viton A: 66% Fluorine

### General Information

|                    |   |
|--------------------|---|
| Compound Number:   | 075F2124  |
| Date:              | December 09, 2022   |
| Origin:            | Made in the USA   |
| Polymer:           | FKM (Fluoroelastomer)   |
| Temperature Range: | -20 to +400°F   |
| Specification:     | N/A   |
| Compliance:        | RoHS & REACH & CA. Prop 65, Manufactured with genuine Chemours Viton. |

### Physical Properties

| Property          | Test Method | Minimum |
|-------------------|-------------|---------|
| Hardness, Shore A | ASTM D2240  | 75 ± 5  |
| Tensile, psi      | ASTM D412   | 1000    |
| Elongation, %     | ASTM D412   | 175     |

West American Rubber Company, LLC  
 750 North Main Street, Orange, CA 92868  
 Tel: 714-532-3355 Fax: 714-532-2238  
 Email: [Sales@warco.com](mailto:Sales@warco.com)

America's Choice for Quality Rubber Since 1910™  
 Where Tradition Meets Innovation™