



Specification Sheet

Custom Product

General Information

Compound Number:	075F0266
Date:	May 20, 2025
Origin:	Made in the USA
Polymer:	FKM (Fluoroelastomer)
Temperature Range:	-20 to +450°F
Specification:	Viton™ GF 70% fluorine content
Compliance:	RoHS & REACH & CA. Prop 65

Physical Properties

Property	Test Method	Typical
Hardness, Shore A	ASTM D2240	75 ± 5
Tensile, psi	ASTM D412	2200
Elongation, %	ASTM D412	220

West American Rubber Company, LLC
750 North Main Street, Orange, CA 92868
Tel: 714-532-3355 Fax: 714-532-2238
Email: Sales@warco.com

America's Choice for Quality Rubber Since 1910™
Where Tradition Meets Innovation™